

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : C03C 13/00	A1	(11) International Publication Number: WO 95/32926	(43) International Publication Date: 7 December 1995 (07.12.95)
---	----	--	---

(21) International Application Number: PCT/EP95/01992

(22) International Filing Date: 24 May 1995 (24.05.95)

(30) Priority Data:

P 44 18 728.9 28 May 1994 (28.05.94) DE  
195 03 171.7 1 February 1995 (01.02.95) DE

(71) Applicant (for all designated States except US): ISOVER  
SAINT-GOBAIN [FR/FR]; Les Miroirs, 18, avenue  
d'Alsace, F-92400 Courbevoie (FR).

(72) Inventors; and

(75) Inventors/Applicants (for US only): ROUYER, Elisabeth  
[FR/FR]; 32bis, rue de l'Alma, F-92600 Asnières (FR).  
DE MERINGO, Alain [FR/FR]; 294, rue Saint-Jacques,  
F-75005 Paris (FR). MAUGENDRE, Stéphane [FR/FR];  
21, rue Gaston Watteau, F-60460 Précy-sur-Oise (FR).  
SAINT-FOI, Daniel [FR/FR]; 56, rue Marcel Duchemin,  
F-60600 Clermont (FR).

(74) Agent: KADOR & PARTNER; Corneliusstrasse 15, D-80469  
München (DE).

(81) Designated States: AU, BR, CA, CN, CZ, FI, HU, JP, KR,  
MX, NO, NZ, PL, SI, SK, US, European patent (AT, BE,  
CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT,  
SE).

Published

With international search report.

(54) Title: GLASS-FIBER COMPOSITIONS

(57) Abstract

A biologically degradable mineral-fiber composition characterized by the following constituents in percent by weight: SiO<sub>2</sub> 45 to 60; Al<sub>2</sub>O<sub>3</sub> less than 2; CaO + MgO 10 to 16; Na<sub>2</sub>O + K<sub>2</sub>O 14 to 20; B<sub>2</sub>O<sub>3</sub> 7 to 18; P<sub>2</sub>O<sub>5</sub> 0 to 4; BaO 1 to 5; Ti, Zr, Zn, Sr, Fe, Mn oxide 0 to 1.5; Diverse up to 0.5.

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Larvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

## Glass-fiber compositions

The present invention relates to a glass-fiber composition that is biologically degradable.

The prior art describes some glass-fiber compositions which are said to be biologically degradable.

The biological degradability of glass-fiber compositions is of great importance because various studies point out that some glass fibers with very small diameters in the range of less than 3 microns are suspected to be carcinogenic, while biologically degradable glass fibers of such dimensions show no carcinogenicity.

However not only the biological degradability is of crucial importance but also the mechanical and thermal properties of the glass fibers, or the products produced therefrom, the resistance of the glass fibers and the processibility of the glass-fiber composition. For example glass fibers are used to a great extent for insulation purposes. For these applications sufficient moisture-resistance is necessary.

Also, the glass-fiber composition must permit processibility by known methods for producing glass fibers with a small diameter, for example the centrifugal technique, in particular the inner centrifugal technique (this technique is described for example in US-PS 4 203 745).

The invention is based on the problem of providing a novel glass-fiber composition that is characterized by biological degradability, has good stability or resistance to moisture and is easy to process.

The invention is based on the finding that this problem can be solved by a glass-fiber composition that substantially has considerable amounts of alkaline-earth oxide, alkali oxide and boron oxide and also contains barium oxide.

It has turned out that such a glass-fiber composition fulfills the combination of the necessary properties, namely

biological degradability, resistance to moisture and good processibility.

The object of the invention is a glass-fiber composition that is biologically degradable, characterized by the following constituents in percent by weight:

$\text{SiO}_2$	45	to 60
$\text{Al}_2\text{O}_3$	less than 2	
$\text{CaO} + \text{MgO}$	10	to 16
$\text{Na}_2\text{O} + \text{K}_2\text{O}$	14	to 20
$\text{B}_2\text{O}_3$	7	to 18
$\text{P}_2\text{O}_5$	0	to 4
$\text{BaO}$	1	to 5
Ti, Zr, Zn, Sr, Fe, Mn oxide	0	to 1.5
Diverse		up to 0.5.

The inventive glass-fiber compositions are processible by the centrifugal technique. The obtained fibers have good resistance to moisture. Surprisingly enough, the glass-fiber compositions show biological degradability. The mean fiber diameter is preferably less than 10 microns and is in particular between 2.5 and 5 microns.

The inventive glass-fiber compositions preferably have the following constituents in percent by weight:

$\text{SiO}_2$	53	to 60
$\text{Al}_2\text{O}_3$	0	to 1.5
$\text{CaO} + \text{MgO}$	10	to 13
$\text{Na}_2\text{O} + \text{K}_2\text{O}$	14	to 18
$\text{B}_2\text{O}_3$	8	to 14
$\text{P}_2\text{O}_5$	0	to 2.0
$\text{BaO}$	1.5	to 3
Ti, Zr, Zn, Sr, Fe, Mn oxide	0	to 1.5
Diverse		up to 0.5.

According to a further preferred embodiment the inventive glass-fiber compositions have the following constituents in percent by weight:

$\text{SiO}_2$	46	to 55
$\text{Al}_2\text{O}_3$	less than 2	
$\text{CaO} + \text{MgO}$	10	to 14
$\text{Na}_2\text{O} + \text{K}_2\text{O}$	14	to 17
$\text{B}_2\text{O}_3$	10	to 17
$\text{P}_2\text{O}_5$	0	to 2.0
$\text{BaO}$	3	to 5
Ti, Zr, Zn, Sr, Fe, Mn oxide	0	to 1.5
Diverse		up to 0.5.

Barium oxide has a positive influence on moisture-resistance and presumably also on biological degradability.

The inventive compositions can contain up to 1.5 percent by weight titanium oxide, zirconium oxide, zinc oxide, strontium oxide, lithium oxide, iron oxide and/or manganese oxide. Mixtures of 2 or 3 of these oxides are particularly preferred.

Phosphorus oxide is preferably present in an amount of 0.1 to 2 percent by weight, in particular 0.3 to 1.5 percent by weight. Phosphorus oxide has a positive influence on biological degradability.

According to a preferred embodiment the composition contains less than 2 percent by weight magnesium oxide.

The moisture-resistance of the inventive glass-fiber compositions was determined by a standard method known as the DGG method. In the DGG method 10 g finely ground glass with a grain size between about 360 and 400 microns is held at the boiling point for five hours in 100 ml water. After quick cooling of the material the solution is filtered and a certain volume of the filtrate evaporated to dryness. The weight of the thus obtained dry material permits the amount

of glass dissolved in the water to be calculated. The amount is stated in milligrams per gram of tested glass.

The biological degradability of the inventive glass compositions was tested by introducing 1 g of the glass powder, as described for the DGG method, into a physiological solution with the composition stated below and a pH value of 7.4:

NaCl	6.78
NH <sub>4</sub> Cl	0.535
NaHCO <sub>3</sub>	2.268
NaH <sub>2</sub> PO <sub>4</sub> ·H <sub>2</sub> O	0.166
(Na <sub>3</sub> citrate) 2H <sub>2</sub> O	0.059
Glycine	0.450
H <sub>2</sub> SO <sub>4</sub>	0.049
CaCl <sub>2</sub>	0.022

Dynamic test conditions were selected as are described in Scholze and Conradt. The flow rate was 300 ml/day. The duration of the test was 14 days. The results are stated as percent of SiO<sub>2</sub> in the solution x 100 after 14 days.

The invention shall be described in more detail in the following with reference to examples.

#### Example 1

A glass of the following composition in percent by weight was melted:

SiO <sub>2</sub>	57.5
Al <sub>2</sub> O <sub>3</sub>	0.5
CaO	8.0
MgO	3.5
Na <sub>2</sub> O	15.8
K <sub>2</sub> O	0.2

- 5 -

$B_2O_3$	12.0
BaO	2.0
Diverse	0.5.

These glass compositions could be processed by the centrifugal technique.

Using the above-described DGG method a value of 40 was determined.

The above-described test for biological degradability yielded a value of 500.

#### Example 2

A glass with the following composition in percent by weight was melted:

$SiO_2$	56.5
$Al_2O_3$	0.5
CaO	8.0
MgO	3.5
$Na_2O$	15.8
$K_2O$	0.2
$B_2O_3$	12.0
BaO	2.0
$P_2O_5$	1.0
Diverse	0.5.

These glass compositions could be processed by the centrifugal technique.

Using the above-described DGG method a value of 40 was determined.

The above-described test for biological degradability yielded a value of 600.

## Example 3

A glass with the following composition in percent by weight was melted:

$\text{SiO}_2$	57.2
$\text{Al}_2\text{O}_3$	0.8
$\text{CaO}$	7.0
$\text{MgO}$	2.0
$\text{Na}_2\text{O}$	18.0
$\text{K}_2\text{O}$	0.5
$\text{B}_2\text{O}_3$	12.5
$\text{BaO}$	2.0.

These glass compositions could be processed by the centrifugal technique.

Using the above-described DGG method a value of 20 was determined.

The above-described test for biological degradability yielded a value of 500.

## Example 4

A glass with the following composition in percent by weight was melted:

$\text{SiO}_2$	57.2
$\text{Al}_2\text{O}_3$	0.8
$\text{CaO}$	8.0
$\text{MgO}$	1.5
$\text{Na}_2\text{O}$	17.5
$\text{K}_2\text{O}$	0.5
$\text{B}_2\text{O}_3$	13.0
$\text{BaO}$	1.5.



These glass compositions could be processed by the centrifugal technique.

Using the above-described DGG method a value of 20 was determined.

The above-described test for biological degradability yielded a value of 600.

## Claims

1. A glass-fiber composition that is biologically degradable, characterized by the following constituents in percent by weight:

$\text{SiO}_2$	45 to 60
$\text{Al}_2\text{O}_3$	less than 2
$\text{CaO} + \text{MgO}$	10 to 16
$\text{Na}_2\text{O} + \text{K}_2\text{O}$	14 to 20
$\text{B}_2\text{O}_3$	7 to 18
$\text{P}_2\text{O}_5$	0 to 4
$\text{BaO}$	1 to 5
Ti, Zr, Zn, Sr, Fe, Mn oxide	0 to 1.5
Diverse	up to 0.5.

2. The glass-fiber composition of claim 1, characterized by the following constituents in percent by weight:

$\text{SiO}_2$	53 to 60
$\text{Al}_2\text{O}_3$	0 to 1.5
$\text{CaO} + \text{MgO}$	10 to 13
$\text{Na}_2\text{O} + \text{K}_2\text{O}$	14 to 18
$\text{B}_2\text{O}_3$	8 to 14
$\text{P}_2\text{O}_5$	0 to 2.0
$\text{BaO}$	1.5 to 3
Ti, Zr, Zn, Sr, Fe, Mn oxide	0 to 1.5
Diverse	up to 0.5.

3. The glass-fiber composition of claim 1, characterized by the following constituents in percent by weight:

$\text{SiO}_2$	46 to 55
$\text{Al}_2\text{O}_3$	1.5 to 4
$\text{CaO} + \text{MgO}$	10 to 14
$\text{Na}_2\text{O} + \text{K}_2\text{O}$	14 to 17

$B_2O_3$	10	to 17
$P_2O_5$	0	to 2.0
BaO	3	to 5
Ti, Zr, Zn, Sr, Fe, Mn oxide	0	to 1.5
Diverse		up to 0.5.

4. The glass-fiber composition of any of claims 1 to 3, characterized in that the composition contains up to 1.5 percent by weight titanium oxide, zirconium oxide, zinc oxide, strontium oxide, lithium oxide, iron oxide, manganese oxide and mixtures thereof.

5. The glass-fiber composition of any of claims 1 to 4, characterized in that the composition contains 0.1 to 2 percent by weight, in particular 0.3 to 1.5 percent by weight, phosphorus oxide.

6. The glass-fiber composition of any of claims 1 to 5, characterized in that the composition contains less than 2 percent by weight magnesium oxide.

## INTERNATIONAL SEARCH REPORT

Internat Application No  
PCT/EP 95/01992A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 C03C13/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 C03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 588 251 (SCHULLER INTERNATIONAL, INC.) 23 March 1994 see claims 1-3; tables 1,2 ---	1-6
A	EP,A,0 019 600 (OY PARTEK AB) 26 November 1980 see claim 1 ---	1-6
A	EP,A,0 412 878 (ISOVER SAINT-GOBAIN) 13 February 1991 see claims --- -/--	1

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*I\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

10 August 1995

Date of mailing of the international search report

31.08.95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patenlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+ 31-70) 340-3016

Authorized officer

Van Bommel, L

# INTERNATIONAL SEARCH REPORT

Internal . Application No

PCT/EP 95/01992

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>GLASTECHNISCHE BERICHTe,  vol. 64, no. 1, January 1991 FRANKFURT  DE,  pages 16-28, XP 000178832  R. M. POTTER ET AL. 'Glass Fiber  Dissolution in a Physiological Saline  Solution'  see page 26 - page 27; table 2  -----</p>	1

## INTERNATIONAL SEARCH REPORT

Internal Application No

PCT/EP 95/01992

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-588251	23-03-94	US-A- 5401693	28-03-95
		CA-A- 2106412	19-03-94
		JP-A- 6321578	22-11-94
-----			
EP-A-19600	26-11-80	SE-B- 418961	06-06-81
		JP-C- 1195154	12-03-84
		JP-A- 56014450	12-02-81
		JP-B- 58024385	20-05-83
		SE-A- 7904044	10-11-80
		US-A- 4312952	26-01-82
		US-A- 4381347	26-04-83
-----			
EP-A-412878	13-02-91	FR-A- 2650821	15-02-91
		FR-A- 2658182	16-08-91
		AU-B- 630484	29-10-92
		AU-A- 6002590	14-02-91
		CA-A- 2022446	12-02-91
		CN-A, B 1049834	13-03-91
		CN-A- 1093066	05-10-94
		DE-D- 69007369	21-04-94
		DE-T- 69007369	13-10-94
		ES-T- 2053139	16-07-94
		HU-B- 210633	28-06-95
		JP-A- 3093650	18-04-91
		PL-B- 165859	28-02-95
		SI-A- 9011548	31-12-94
		US-A- 5108957	28-04-92
		US-A- 5250488	05-10-93
-----			